



SALASARTAN- SBLE

(Synthetic tanning agent for white leather)

Classification :

A synthetic light fast replacement tanning agent for white leather and pastel shade leather

Features:

- SALASARTAN-SBLE has great affinity for the reactive groups of the collagen which facilitates good exhaustion from the bath, remarkable fullness and fine grain pattern of leather.
- Compatible with all syntans and vegetable extracts. When used in conjunction with vegetable extracts, it makes the colour very much lighter.
- Recommended for white leather owing to its non-yellowing property after mild exposure.
- Due to its high tanning power it can be used as solo tanning agent in reptile items and natural coloured leather goods.
- Imparts good fullness, elastic and smooth grain, which can be finely buffed for nubuck and C.G. leathers

Packing Available in:

(Powder) 25 Kgs. LDPE Bag

Disclaimer:

The above information presented is for just basic guidance. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

CHARACTERISTICS :

Chemical Composition	: Phenolic condensation product
Physical Appearance	: Off white coloured Powder
pH (10% Dilution)	: 3.0 - 4.0
Concentration	: 95% min
Acidity	: 5% max
Solubility	: Soluble in water

Application:

- For retanning of white upper leather recommended dosage is 5-6 % on shaved weight.
- For retanning of drum dyed shoe upper leather recommended dosage is 5-6 % on shaved weight.
- In vegetable tannages pre-treatment with 2% SALASARTAN-SBLE will improve the colour of the V.T leather and quickens penetration of vegetable tanning.
- In retannage and bleaching of vegetable tanned leathers, it is advisable to wet back the V.T. leather, prior to retanning. Recommended dosages are 5-8% on shaved weight. Bleaching effect can be increased by adding 1% SALASARTAN-SBLE in fat liquoring bath.
- In retanning of softy Nappa, clothing Nappa for garment leather excellent results is obtained by using SALASARTAN-SBLE 4-5% on shaved weight. In the same bath it is possible to carryout pefatliquoring and carry on with the dyeing and fat liquoring.
- In processing of chrome split leather for white sport shoes, recommended dosages is around 6% on shaved weight.