



# SALASARTAN - P-R7

(Amino resin based tanning agent for the leather industry)

## Classification :

Anionic synthetic resin tanning agent for the retannage of all types of Chrome leathers.

## Properties:

- SALASARTAN- P-R7 has a selective filling action and is mainly deposited in the loose structured parts of the leather.
- Improves the fullness of chrome leathers and tightens the grain at the same time, thus retaining the chrome characteristics. Due to its non-astringent nature there will not be any drawn grain effects.
- Imparts good level dyeing properties and gives retanned leather a brownish colour. Due to its resinous nature it gives a desirable buffing surface.

## Applications:

- It can be used alone or in combination with synthetic, vegetable, chrome tanning material and is best used in undissolved form in short float.
- For retanning of full grain or corrected grain upper leather recommended dosages is 4-5% on shaved weight.
- 2-4% of P-R7 on shaved weight is sufficient for garment leather.

## Characteristics :

Chemical Composition	: Amino resin blended with anionic dispersant and inert fillers
Appearance	: Light brown coloured free flowing powder
pH (10% Dilution)	: 9.0 - 10.0
Concentration	: 95% min.
Solubility	: Soluble in water with slight sediments

## Packing Available in:

(Powder) 25 Kgs. HDPE Bag

## Disclaimer:

The above information presented is for just basic guidance. We recommend that the prospective users determine the suitability of our materials and suggestions before adopting them on a commercial scale.